

SPECIFICATION OF BASIC RAMMING MASS AND GUNNING **MATIERLAS**

BASIC RAMMING MASS AND GUNNING MATERIALS

PRODUCT	MgO	SiO2	Cr2O3	SETTING	GRADING (MM)	SINTERING TEMPERATURE (DEG. C.)	APPLICATION TEMPERATURE (DEG. C.)
MCL RAM 84	84.0	-	-	CERAMIC	0-5	1550	1750
MCL FET 84	84.0	-	-	CERAMIC	0-5	1500	1750
MCL GUN 85	85.0	6.5	-	CHEMICAL/CERAMIC	0-4	1500	1750
MCL RAM 86	86.0	-	-	CERAMIC	0-5	1550	1750
MCL RAM 90	90.0	5.0	-	CERAMIC	0-5	1550	1750
MCL RAM 95	95.0	2.5	-	CERAMIC	0-5	1550	1750
MCL GUN 88	88.0	-	-	CERAMIC	0-3	1550	1750
MCL GUN 92	92.0	5.0	-	CERAMIC	0-3	1550	1750
MCL GUN 95	94.0	2.5	-	CERAMIC	0-3	1550	1750